

LOXEAL 30-12

UV lepidlo sklo - termoplast (PC, PET, PVC, ABS, PMMA)

Vytvrzen 4mW/cm²

PC <30s

PET <10s

PMMA <10s

pevnost ve smyku 7 N/mm²

pevnost ve smyku 4 N/mm²

pevnost ve smyku 3 N/mm²

Tvrdost 60-70Sh

Pevnost v tahu 15-25 N/mm²



TECHNOLOGY
glass paint & equipment